


Leeson ReKote System

COATING (PU5036)



DESCRIPTION


UV resistant polyurethane coat based on 1 component moisture triggered technology. Available in a range of colours.

USES


Renovation of PVC coated metal cladding

BENEFITS


- Fast curing
- UV Stable
- Low viscosity and convenient working time
- Can be brush or spray applied




CM6 Brick Red



CM9 Dark Green




CM7 Safety Yellow




Substrate


Primer



CM5 Dark Grey



CM4 Mid Grey



CM2 Mid Blue

Leeson ReKote System

COATING (PU5036)



PRODUCT SPECIFICATION

Product: Leeson ReKote System

Thickness: Typically 75-150 DFT

Manufacturer: Leeson Polyurethanes Ltd.

Telephone: + 44 (0) 1926 833367

SUBSTRATE REQUIREMENTS

The substrate should be dry to 75%RH as per BS8204 and free from rising damp. Surface should be free of any loose material, and primer may be required, e.g. PU5109 or PU5015 on certain substrates.

PRODUCTS INCLUDED IN THIS SYSTEM

Primer: Aluminium Primer (PU5015) 50-70 DFT

Red Oxide Primer (PU5109) 50-70 DFT

Sealing Coat: Leeson ReKote (PU5036) 75-150 DFT

Detailed installation instructions are available on request.

INSTALLATION SERVICE

The installation should be carried out by an experienced contractor, details of contractors in your area can be obtained by contacting the company

IMPORTANT NOTE

Leeson Polyurethanes' products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request.

TECHNICAL INFORMATION

The figures below are typical properties achieved in laboratory tests at 21°C and 55% Relative Humidity.

Temperature Resistance

Resistant to temperatures of over 70°C for long periods.

Chemical Resistance

To various acids, diesel and petrol as well as strong bases.

Elongation @ Break

min 200% to BS2782 Part 3

Tensile Strength

Min 18 N/mm² to BS2782 Part 3

Speed of Cure

19°C

Touch Dry 4 hours

AFTERCARE - CLEANING AND MAINTENANCE

The surface should be cleaned regularly.

ENVIRONMENTAL IMPACT

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning. Environmental and health considerations are controlled during manufacture of the products by Leeson Polyurethanes staff.

FURTHER INFORMATION

To ensure you are specifying a fit for purpose surface for your project please consult our Area Sales Manager for your area or visit our website.

{ A bond for life }