

Leeson Fast Curing Hygienic Flooring System



COATING (PU5296/ PU5285)



DESCRIPTION


Non-hazardous, fast curing self-smoothing resin for industrial and commercial flooring.

USES


Wash rooms; Commercial Kitchens; Car-parks; Clean Rooms; Hospitals; Laboratories.

BENEFITS


- Attractive appearance
- Anti-slip
- Provides sealing of floors
- Fast Curing
- Chemical Resistant




Red



Green




Orange




Sealer (5285)

Substrate


Bodycoat (5296)



Dark Grey



Light Grey



Blue



Leeson

Fast Curing Hygienic Flooring System

COATING (PU5296/ PU5285)



PRODUCT SPECIFICATION

Product: Leeson Fast Curing Flooring System

Thickness: Typically 0.3-0.5mm

Manufacturer: Leeson Polyurethanes Ltd.

Telephone: + 44 (0) 1926 833367

SUBSTRATE REQUIREMENTS

The substrate should be dry to 75%RH as per BS8204 and free from rising damp.

Concrete: Primer must be used. Minimum 25N/mm², free from laitance, dust and other contamination.

PRODUCTS INCLUDED IN THIS SYSTEM

Primer:	Self Priming	
Body Coat:	PU5296	0.25kg/m ²
	Decorative Aggregate	0.6kg/m ²
Sealing Coat:	PU5285	0.25kg/m ²

Detailed installation instructions are available on request.

INSTALLATION SERVICE

The installation should be carried out by an experienced contractor, details of contractors in your area can be obtained by contacting the company.

IMPORTANT NOTE

Leeson Polyurethanes' products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request.

UV DISCOLOURATION

The system is based on high performance, UV stable technology.

TECHNICAL INFORMATION

The figures below are typical properties achieved in laboratory tests at 21°C and 55% Relative Humidity.

Temperature Resistance

Resistant to temperatures of up to 50°C for long periods.

Chemical Resistance

To various acids, diesel and petrol as well as strong bases.

Elongation @ Break (PU5285)

min 92% to BS2782 Part 3

Tensile Strength (PU5285)

Min 17.5 N/mm² to BS2782 Part 3

Speed of Cure 19°C

90 minutes

Installation Cycle Time

From completion of surface prep to cure including anti-slip sealer 5 hours.

AFTERCARE - CLEANING AND MAINTENANCE

The surface should be cleaned regularly.

ENVIRONMENTAL IMPACT

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning. Environmental and health considerations are controlled during manufacture of the products by Leeson Polyurethanes staff.

FURTHER INFORMATION

To ensure you are specifying a fit for purpose surface for your project please consult our Area Sales Manager for your area or visit our website.



Leeson Polyurethanes Ltd.

Hermes Close, Warwick, CV34 6RP, UK.

Tel: +44 (0) 1926 833367 Fax: +44 (0) 1926 881469
sales@lpultd.com | www.lpultd.com

{ A bond for life }