



PU Anti-Skid for Roads

Leeson Grip 3-1

COATING (PU4490/20)



DESCRIPTION

A high performance, flexible polyurethane based anti-skid system for decorative applications. The system gives a hard wearing anti-skid surface.

USES

Cycle Paths; Pedestrian Areas;

Walkways; Drives; Pathways

BENEFITS


- Anti-Skid Surface
- Bonding of Decorative Aggregates
- High Build System
- Fast Curing
- Excellent Wear Performance
- No odour
- Resistant to oil, diesel & petrol

Decorative Aggregate

Leeson Grip 3-1 PU

Primer (if required)

Substrate



PU Anti-Skid for Roads

Leeson Grip 3-1

COATING (PU4490/20)

PRODUCT SPECIFICATION

Product: Leeson Grip 3-1 (PU4490/20)
Thickness: 2-3mm of PU Resin
Manufacturer: Leeson Polyurethanes Ltd.
Telephone: + 44 (0) 1926 833367

SUBSTRATE REQUIREMENTS

The substrate should be dry to 75%RH as per BS8204 and free from rising damp.

Asphalt: No primer required.

Concrete: Primer must be used. Minimum 25N/mm², free from laitance, dust and other contamination.

PRODUCTS INCLUDED IN THIS SYSTEM

Primer:	Conprime-2 (E4568)	0.25kg/m ²
	Chelford 52 Sand	1kg/m ²
	Or PU3922 PU primer	
Bonding Coat:	Leeson Grip 3-1 (PU4490/20)	2.5-3kg/m ²
Aggregate:	Decorative Aggregate	

Detailed installation instructions are available on request.

INSTALLATION SERVICE

The installation should be carried out by an experienced contractor, details of contractors in your area can be obtained by contacting the company.

IMPORTANT NOTE

Leeson Polyurethanes' products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request.

TECHNICAL INFORMATION

The figures below are typical properties achieved in laboratory tests at 21°C and 55% Relative Humidity.

Temperature Resistance

Resistant to temperatures of over 70°C for long periods.

Chemical Resistance

To various acids, diesel and petrol as well as strong bases.

Tensile Strength (3-1)

8 N/mm² to BS2782 Part 3

Elongation @ Break (3-1)

19% to BS2782 Part 3

Bond Strength

Greater than the cohesive strength of the concrete, >3 N/mm²

Speed of Cure

Traffic Ready: 2 hours @ 20°C

AFTERCARE - CLEANING AND MAINTENANCE

Clean as required, remove any loose aggregate after initial traffic.

ENVIRONMENTAL IMPACT

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning.

Environmental and health considerations are controlled during manufacture of the products by Leeson Polyurethanes staff.

FURTHER INFORMATION

To ensure you are specifying a fit for purpose surface for you project please consult our Area Sales Manager for your area or visit our website.

{ A bond for life }